



Aquacrete®

DustBoss



PRODUCT DATASHEET

Advanced dust management solution

For dust-sensitive areas that require the confidence of our Wet-Repel® brand, combined with an innovative application process that suppresses dust.

Aquacrete® DustBoss is a wet-mix product designed for ventilation control and geology consolidation in underground mines. Formulated to minimise dust creation in underground environments, Aquacrete® DustBoss maintains ventilation air quality and safety during application.



Aquacrete®

DustBoss



FEATURES

- Does not shrink during curing.
- Can be applied to any thickness in a single application.
- Achieves specified overpressure rating in 24 hours.
- Excellent adhesion to various substrates.
- Provides a water-resistant seal.
- High early strength for reliable short and long-term use.
- Compressive strength up to 25 MPa.
- Wet mix application eliminates potential dust generation.
- Non-slumping.

APPLICATIONS

- Water-retaining bulkheads
- Dam walls
- Explosion-rated ventilation seals and stoppings
- Backfill containment walls
- Strata consolidation
- Stopping and seal repairs
- Overcast and overcast wings.

PERFORMANCE

Aquacrete® DustBoss is designed for efficient, dust-free application. With anti-static and fire-resistant properties, it can be applied to any thickness in a single application. It has a non-slumping formula and strong adhesion, achieving its specified overpressure rating and forming a water-resistant seal after 24 hours.

Structures can be engineered to meet site-specific overpressure requirements in excess of 100 psi.

PACKAGING/HANDLING/STORAGE

Aquacrete® DustBoss is available in:

500kg bulker bags 2 bags per pallet

1 tonne bulker bags 1 per pallet

For optimal performance, store in its original, unopened packaging in a dry, covered area.

QUALITY CONTROL

To ensure Aquacrete® DustBoss meets the highest industry standards and specified engineering properties, it is tested and certified by the National Association of Testing Authorities

(NATA). Please contact us if you require a copy of the relevant certificates.

TECHNICAL SPECS

Form	Granular powder
Colour	Off-white
Bulk density	1400kg/m ³
Compressive strength at 2 days	17MPa
Compressive strength at 3 days	21.2MPa
Compressive strength at 7 days	23MPa
Compressive strength at 28 days	29.7MPa
Flexural strength at 28 days	4.8MPa
Flammability	Non-flammable / anti-static

DISCLAIMER

Performance test results are provided as a guide and may vary depending on site conditions, application methods, installer expertise, and general job site care.

We recommend that users assess the suitability of our products for their specific environment and application. For questions about product specifications, intended use, or best application practices, please contact our technical team at 0417 818 004.

For further details, please refer to the Safety Data Sheet.

Copyright© 2025 Central Gypsum PTY Ltd.



For more information about Aquacrete® products call 0417 818 004,
email sales@aquacrete.com.au or visit aquacrete.com.au

